


edelweiss CAD/CAM BLOCK T-BLOCK/C-BLOCK/i-BLOCK

*Explore a single glass-phase embedded in a hybrid matrix
developed by the patented edelweiss laser sintering process*

■ **Minimally Invasive** ■ **Bio Esthetic** ■ **Bio Functional**



Bio-Esthetics and function in one appointment


edelweiss dentistry is a “think tank” driven by inspiration and technical know-how that conceptualizes and produces innovative systematic solutions that are developed together with partners within the dental industry and marketed via an exclusive dental distribution network. The edelweiss CAD/CAM BLOCKs are state of the art for modern and minimally invasive esthetic dentistry.

The new edelweiss CAD/CAM BLOCK has an homogeneous base material of glass (silica) manufactured through a patented process of controlled laser sintering technology fusing the glass crystals. The finished product is characterized by a single glass phase embedded in a hybrid matrix. The properties of both particle reinforced and predominately glass ceramics are featured in a single hybrid glass block, having the strength of reinforced ceramics, the optical properties of predominantly glass ceramics and the flexibility of dentin. Its versatile application together with its time and cost saving procedure makes the edelweiss CAD/CAM BLOCKs a sound investment in the future with the best interest of the patient in mind. Convince yourself.



Stephan Lampi
CEO, Founder & Inventor
of edelweiss dentistry

Desigar Moodley
Chief Scientific Officer
of edelweiss dentistry



New Era of Design in CAD/CAM Blocks

BREAKTHROUGH IN CAD/CAM MATERIALS


edelweiss dentistry presents a breakthrough in the fabrication of CAD/CAM materials. Through a process of laser sintering and vitrification, edelweiss has developed state of the art CAD/CAM blocks. Through this process, the finished product consists of a single glass-phase embedded in a hybrid matrix. As a result, the esthetic properties are similar to that of feldspathic glass ceramic without having the brittleness of pure ceramics.

SILICA AND BARIUM GLASS AS A BASE

The base material of the edelweiss block is glass, in which crystals are joined by controlled laser sintering. The edelweiss CAD/CAM BLOCK is mainly composed of silica and barium glass with a very small portion of resin, combining the added advantages of ceramic and polymer materials into one block.

STRONG BUT FLEXIBLE

The strength and optical properties are similar to that of ceramics but maintaining the flexibility and repairability of polymer based materials. The addition of zinc oxide nanoparticles and fluoride provides antibacterial properties, a unique feature of the edelweiss CAD/CAM BLOCK.



edelweiss
CAD/CAM BLOCK

Manufacturer B
CAD/CAM Block



VISUAL COMPARISON

edelweiss CAD/CAM BLOCK exhibits natural translucency, with light reflection showing an extremely glossy surface. The edelweiss blocks are more translucent

than other blocks giving a more natural appearance which may be attributed to the aluminium oxide and barium silicate glass.

KEY FEATURES

- Glass as a single phase for esthetics
- Silica glass plus Aluminium oxide for compressive strength
- Hybrid matrix for elasticity
- ZnO and F⁻ for biocompatibility strength



Technical Data	CAD/CAM BLOCK
Flexural Strength Biaxial	320 MPa
Flexural Strength Three Point	200 MPa
Compressive Strength	550 MPa
Flexural Modulus	20 GPa
Surface Hardness	100 HV


(Source: Technical data from manufacturer's documentation)

Size & Color

T-BLOCK
Translucent Enamel

i-BLOCK Implant
Translucent Enamel & Chroma

C-BLOCK
Chroma



1 ENAMEL TRANSLUCENT SHADE

4 DENTIN CHROMA: These are highly translucent blocks that mimic the natural enamel in optical properties while the underlying dentin shade can then be duplicated through the use of various resin composite/cement shades. This can be further individualized by varying the composite shades according to cervical and incisal color variations in the natural tooth.

SHADES (A0, A1, A2, A3)

C-BLOCK (Chroma): These are highly chromatic blocks that correspond to shades A0, A1, A2 and A3.

AVAILABLE IN STANDARD SIZES

12 x 14 x 18 mm
10 x 12 x 16 mm




INDIVIDUAL CHARACTERIZATION

Individual characterizations can be also accomplished using edelweiss EFFECT SHADES or other resin-staining kits.

Clinicians are now in complete control of the final esthetic outcome by being able to adjust the final shade matching and

characterizations according to the patient's needs, thereby eliminating any errors in shade matching.



Advantages & Indications



Marco Tudts

Head of Advisory Board CAD/CAM
edelweiss dentistry

THE BEST FOR YOUR PATIENTS

“The uniqueness of edelweiss CAD/CAM BLOCKs lies in the manufacturing process where through the patented vitrification and laser sintering process a state of the art hybrid glass block is manufactured. This ensures the edelweiss CAD/CAM BLOCK combines the properties of current CAD/CAM systems into one single block. It resembles the esthetics of a feldspathic glass, the strength of particle infiltrated ceramic and the resilience and ease of reparability of composite blocks.”


“The difference lies in the high similarity with nature.”

ADVANTAGES


- Ultrafine sintered glass microstructure combines high strength with permanent high gloss
- Shorter milling time
- Kinder to the milling burs
- No additional firing required, simply polish and cement
- Simple cementation procedure with proven perfect seal
- Cost saving, faster processing time reduces chairside time
- Biomechanical and biocompatible
- Esthetically superior, life-like appearance
- Restoration can be easily fine tuned or repaired by the dentist

INDICATIONS


THIN VENEERS / VENEERS




ANTERIOR / POSTERIOR CROWNS




OCCLUSAL VENEERS




IMPLANT CROWNS




INLAYS



ONLAYS




PARTIAL CROWNS




SEM Analysis of edelweiss CAD/CAM BLOCKS


EDELWEISS CAD/CAM MILLING BLOCK



The edelweiss CAD/CAM BLOCK shows an homogenous layer of glass almost fused to form a single unit. There is a complete absence of voids or defects on the surface structure. (Mag = 3.00KX)



Higher magnification shows absence of any surface defects or voids, ensuring long lasting color stability and no chipping or crack propagation. (Mag = 7.66KX)



(Mag = 15.05KX)


Through back scatter, the individual glass particles seem fused into a single mass devoid of any voids or defects. Unlike observed with other CAD/CAM blocks there are no cracks or defects within the material itself.

This makes the material more stable under occlusal forces preventing any fractures and better wear resistance. The absence of surface voids and defects makes the edelweiss CAD/CAM BLOCK more color

stable preventing surface staining. This is also important during the milling process resulting in smoother margins of the finished restorations and a much "softer" feel on the CAD/CAM milling bur.

Milling time is much shorter and the milling bur lasts much longer than when used with other blocks. This results in smoother chip free margins and a more polished surface.

ELEMENTAL ANALYSIS



The composition of edelweiss CAD/CAM BLOCKS are mainly barium/silicate glass, zinc oxide nanoparticles, carbon, aluminium oxide and fluoride.

Barium silicate glass provides a single glass phase for optimum esthetics and ensures adequate bonding to the tooth structure using the edelweiss bonding system.


Aluminium oxide provides additional strength and improves the optical properties of the CAD/CAM BLOCK.

The addition of zinc oxide nanoparticles provides antibacterial properties preventing any plaque accumulation on the surface of the material.


Fluoride enables possible hydroxyapatite regeneration if required. The addition of ZnO and F⁻ is unique to the edelweiss CAD/CAM BLOCKS.

SEM Analysis of Alternative CAD/CAM Blocks


PRODUCT B CAD/CAM MILLING BLOCK



The SEM of product B CAD/CAM block shows an inhomogeneous surface structure possibly due to it being a composite/ceramic hybrid. Several voids and cracks appear on the surface. (Mag = 2.83KX)



Irregularly shaped structures are easily observed on the surface presenting an uneven surface. (Mag = 15.27KX)




The product B blocks contain fine spicules that seem to be protruding from the surface. (Mag = 14.65KX)

PRODUCT C CAD/CAM MILLING BLOCK



Product C shows a mottled appearance with gaps within the material itself. (Mag = 64X)

PRODUCT D CAD/CAM MILLING BLOCK



Product D CAD/CAM shows an inhomogeneous surface with irregular shaped structures. Several gaps and voids are seen on the surface. (Mag = 6.72KX)

SEM done by Prof. Lydia-Marie Joubert (PhD, MPhil), Central Analytical Facilities, University of Stellenbosch, South Africa
All Rights Reserved. edelweiss dentistry products gmbh • Austria.

CONCLUSION

SEM shows the compactness in the structure of the edelweiss CAD/CAM BLOCKS. This ensures minimal chances of crack propagation under normal occlusal forces.

The geometry of the glass crystals within the material is similar to natural enamel enabling proper light scattering for optimal esthetics.

Optical properties of edelweiss CAD/CAM BLOCKS show superior esthetic properties due to the pure glass structure and aluminium oxide.

edelweiss CAD/CAM BLOCKS come with the added advantage of the inclusion of zinc oxide and fluoride making it antibacterial.

Clinical Comparison: Two CAD/CAM Systems in one patient



edelweiss VENEERS (11, 12 and 13).

SPLIT-MOUTH CLINICAL STUDY: ONE WEEK AFTER TREATMENT

- edelweiss VENEERS maintain its original gloss as a result of its single hybrid glass phase.
- The veneers have a shiny appearance giving it a more natural enamel life-like appearance.




TWO WEEKS AFTER TREATMENT


- edelweiss VENEERS still have its glass like shiny appearance maintaining its original gloss.
- There is no sign of wear or abrasion as a result of tooth brushing.
- There is no loss of surface anatomy. Original line angles and surface characterizations still present.

THREE WEEKS AFTER TREATMENT

- Long lasting gloss can still be seen after 3 weeks.
- There are no signs of abrasion or loss of surface anatomy.
- Proper canine guidance can still be observed with no wear facets on the canine veneer.

- Patient says, "The veneers on the right side feel like his original teeth, a very smooth and polished surface".
- Higher magnification shows a very smooth glossy surface devoid of any surface roughness or scratches.






Alternate veneers (21, 22 and 23).

**SPLIT-MOUTH CLINICAL STUDY:
ONE WEEK AFTER TREATMENT**

- Alternate veneers seem to lose its original lustre.
- It appears dullish having a more opaque look.
- The dispersed particles within the resin matrix may account for the loss of the original shine over time.




TWO WEEKS AFTER TREATMENT

- Alternate veneers become duller over time, looking more opaque.
- Some of its original surface anatomy is lost. Original surface contours seem to have been smoothed out.
- Fine micro abrasions start to appear on the surface possibly a result of tooth brush wear on the veneer.




THREE WEEKS AFTER TREATMENT


• Patient says, "The veneers on left side feel rough and is not as smooth as the right side of his mouth. It also has a dullish appearance".



• Veneer on tooth 21 chipped on incisal margin, extending to buccal side. It is a cohesive fracture occurring within the material itself.




• Veneer on tooth 23 chipped on mesio-incisal margin. The fracture extends to buccal wall of the veneer.



• Fractures may possibly be a result of the weakness of the material itself. The material cannot withstand occlusal forces because of its lower micro-hardness and elastic modulus values.

• Higher magnification shows a rough surface with scratches.




Alternative

Step by Step/ Cementation of Restoration




1 The attachment point of the block is smoothed out with fine-grain diamond burs. Final polish is achieved using cotton /linen buffs.



2 Coat the prepared fitting surface of the edelweiss restoration with edelweiss VENEER Bond using an applicator tip/microbrush and rubbing it gently. Dry edelweiss VENEER Bond using an oil and water free stream



of air, so that a slightly moist surface of the edelweiss restoration without any pooling of the VENEER Bond. Light cure edelweiss VENEER Bond for at least 20 seconds using a light curing device.



3 An appropriate amount of the composite is softened using the finger tips, pressed into a ball and inserted into the restoration. With a spatula instrument the composite is pressed onto the inner surface of the restoration to form a thin layer of cement.




4 Apply 37 % phosphoric acid gel to the prepared tooth. The etchant should be left to react on the enamel for 15-30 sec. and on the dentin for 10-15 sec. Rinse thoroughly with water and gently dry.




5 Starting with the enamel, thoroughly coat the tooth surfaces to be treated with Dentin Bonding Agent/Adhesive. The adhesive must be gently applied to the tooth surface for at least 20 sec. and light cured for 20 sec. in all directions.



6 After placing an appropriate amount of the composite cement into the restoration, gently seat the restoration onto the prepared tooth surface and retain it in place exerting uniform pressure. Remove all excess composite material.




7 Cleaning and removing any excess cement from the interdental areas using dental floss.



8 Final light-cure for 20 sec. on all surfaces and margins with a curing unit with light intensity of 1000 mW/cm².



9 After having adhesively cemented the restoration, adjust occlusion/articulation with suitable grinding instruments.



10 Work the interproximal areas with finishing strips then polish with polishing strips.



11 Final polishing is done with a silicone cup especially around the margins of the restoration. This will ensure a very high gloss surface.

Perfect Bonding & Blending with edelweiss System Components

edelweiss VENEER BOND

is used to provide adhesion to the glass phase/resin component of the edelweiss CAD/CAM restoration and has been shown to provide optimal bonding across the entire surface. The bond between the restorative interface and the tooth is enhanced through the use of edelweiss NANO-HYBRID COMPOSITE or edelweiss NANO-HYBRID FLOWABLE COMPOSITE.

PERFECT MARGINAL ADAPTION

Since the edelweiss CAD/CAM restoration and the edelweiss cement have the same composition it acts as a monobloc ensuring a perfect marginal seal. In-vitro studies have shown no marginal leakage on both enamel and dentin interfaces when cemented with edelweiss bonding systems.

PERFECT STAIN FREE MARGINS

In the case of the edelweiss bonding system sub-margination or ditching at the tooth interface is non-existent as the cement and the restoration are one system. Staining is completely absent with the edelweiss bonding system.

PERFECT MARGIN COLOR MATCH

The monobloc system ensures there will be no color difference between the restoration and tooth surface at the cementation interface. The edelweiss cement and the edelweiss restoration have the same composition and optical properties, hence no unsightly restoration margins are visible.

Please note:

Cementation can also be achieved using conventional resin luting cements, however, for optimum results it is recommended to use edelweiss components.



VENEER BOND

edelweiss VENEER Bond is a light curing adhesive for bonding edelweiss restorations and for intraoral repairs to damaged restorations.



NANO-HYBRID COMPOSITE

edelweiss NANO-HYBRID COMPOSITE is a light-curing, radiopaque, highly filled nano-hybrid composite filling material for restorations or cementation that meet the highest standards.



NANO-HYBRID FLOWABLE COMPOSITE

edelweiss NANO-HYBRID FLOWABLE COMPOSITE is a light-curing, radiopaque filling material for restorative therapy or for cementation.




EFFECT SHADE

edelweiss EFFECT SHADE is a light-curing, thin-flowing composite which has been specifically developed for the characterization of restorations. Due to the special pigmentation, Effect Shades allow color individualization of restorations.

One Session – Change for a Lifetime

YESTERDAY

TODAY



Bruxism

Patient was worried about her teeth being worn down and discoloured. Following splint therapy to treat the bruxism, the teeth were restored using edelweiss T-BLOCKS and NANO-HYBRID COMPOSITE A2 to the new vertical height.



YESTERDAY

TODAY



Deep bite with diastema

Patient was concerned about the midline gap between the two front teeth. The vertical dimension was increased following the use of splint therapy. Restorative treatment was followed with edelweiss CAD/CAM T-BLOCKS and cemented with edelweiss NANO-HYBRID COMPOSITE A1.



YESTERDAY

TODAY



Retroclined teeth

Patient was concerned about the way her teeth were positioned and was conscious of her smile. Her teeth were slightly retroclined and this was corrected using edelweiss CAD/CAM T-BLOCKS to mill ultra thin veneers and cemented using edelweiss NANO-HYBRID COMPOSITE A1.



YESTERDAY

TODAY



Old defective restorations

Patient presented with defective restorations and compromised esthetics. Because of the translucent nature of the edelweiss T-BLOCKS, the restorations blended in with the shade and vitality of the natural surroundings whilst using the least invasive method of restoring the teeth.



edelweiss CAD/CAM BLOCK

i-BLOCK

i-BLOCK FOR IMPLANT SOLUTIONS

edelweiss i-BLOCKS are CAD/CAM blocks used for precise and reliable fabrication of implant-supported restorations. Manufactured from a patented laser sintering process to produce a single hybrid glass phase ensuring optimum esthetics and exceptional strength with long lasting polish and wear resistance.

■ *biological* ■ *functional* ■ *esthetic*



PRECISE INTERFACE INTEGRATION



With the new edelweiss i-BLOCK, you can now create customized abutments and crowns. This allows the quick and safe restoration of implants. The edelweiss i-BLOCK can be easily integrated into the practice's digital workflow.

12 x 14 x 18 mm



Precision manufacturing processes guarantee the new edelweiss i-BLOCKS fit precisely onto Titanium Base (TiBase or similar attachments) so that the final restoration can be placed in the same appointment, reducing treatment sessions and improving the patient experience.

INDICATIONS WITH TWO SIMPLE SOLUTIONS


The edelweiss i-BLOCK can be used as screw retained single abutment crowns as well as for mesostructure (abutment) and final crowns. This ensures a perfect emergence profile for optimal esthetics. Its antibacterial properties and a good mucosal seal helps prevent peri-implantitis thereby protecting the implant.



■ *Single unit as abutment crown*



■ *Mesostructure and crown*



WHY EDELWEISS CUSTOM ABUTMENTS?

The edelweiss custom abutments offer several advantages over stock abutments, including:

- Patient-specific soft tissue management that conforms precisely to the patient's gingival contours, makes them an excellent biologic and esthetic option for implant treatment.
- The edelweiss custom abutments offer a tissue-level cement junction compared to subgingival location of the cement junction seen in a typical stock abutment.
- The two-piece structures provide stability to the components, and are very easy to use.
- The edelweiss abutment crown (TiBase + crown) can be simply screwed on to the implant.
- The edelweiss crown and the TiBase can be assembled extra-orally. This avoids any problems that may arise due to unclean adhesive surfaces.
- The edelweiss abutment is antibacterial offering exceptional biocompatibility in the oral mucosa.
- The edelweiss abutments guarantee optimal esthetics resembling dentin shades with the final crown mimicking that of natural enamel.
- In-Office Fabrication – With CAD/CAM dentistry, the ultimate benefit is the ability to fabricate this in the office the same day. With edelweiss i-BLOCK you don't need an expensive sintering furnace like you would for most other materials.
- The edelweiss i-BLOCK is time and cost-efficient.

UNIQUE PROPERTIES

edelweiss i-BLOCK has unique built in antibacterial properties. It is the only block with this feature. Through a patented manufacturing process, zinc oxide nanoparticles are added to the material ensuring optimal periodontal health. It also contains fluoride to prevent any plaque accumulation on the crown. The edelweiss i-BLOCK has perfect form to maintain the mucosal seal thus protecting the implant against peri-implantitis.

edelweiss i-BLOCK has a unique shock absorbing effect. Resin within the material provides resilience to the restoration having a shock absorbing effect to withstand any occlusal stresses. This is particularly important to avoid stresses being transmitted to the periodontal tissues, the implant, the opposing tooth or the TMJ. Having a modulus of elasticity of 20 GPa ensures it behaves similar to dentin, absorbing all stresses within the material.

edelweiss i-BLOCK offers the ultimate in esthetics, it allows you to create a custom abutment that is shaped and shaded like dentin. It allows for a more translucent enamel-like material over the abutment for optimum esthetics. The margin can be placed supragingival ensuring optimum gingival health. Esthetically there is no more of the grayish prefabricated abutment shining through.

COMPATIBILITY

edelweiss i-BLOCKS are compatible with systems of the providers via the TiBase interface like Dentsply Sirona, Nobel Biocare, Straumann, etc.





Clinical Case



*Clinical case: Dr. Marco Tudts
D.D.S, M.Sc.D*

MODEL BASED DIGITAL WORKFLOW

- Plaster model was prepared.
 - Lab analogue was placed on the preferred implant position on the model for an ideal implant crown position.
 - Surgical placement of implant was done.
 - Implant crown placed on the same position as in the plaster model.
1. Intra oral scan of the initial situation was made using Primescan
 2. A 3D model was printed
 3. A 3D planning was done using CEREC software
 4. The CEREC guide was designed to place the implant lab analogue
 5. The implant lab analogue was placed on the model and scanned
 6. The base (edelweissi-BLOCK) + the crown (edelweiss C-BLOCK) was designed in the CEREC software
 7. The base substructure and the crown was milled
 8. The TiBase + edelweiss Base + edelweiss Crown was checked on the model for fit
 9. Using the template the implant was placed in the ideal position in the mouth
 10. The implant supported crown was attached to the implant
 11. Proper seating of the implant crown was checked with a control X-ray
 12. Final occlusion was checked
 13. Patient recall and follow up for implant maintenance








IMMEDIATE LOADING DIGITAL WORKFLOW

Everything is done chairside from:

- Intraoral scanning
- 3D surgery planning
- 3D guide design planning
- 3D milling of the guide
- Surgical implant placement
- Immediate loading of the pre-designed implant supported crown.

1. Initial clinical situation was scanned using Primescan
2. CBCT taken using AXEOS 3D imaging system
3. The Dicom and STL files were merged
4. A segmentation and virtual extraction of the tooth was done
5. The virtual implant and crown was planned in SICAT
6. The SICAT virtual 3D planning was exported to CEREC software
7. A 3D surgical guide was made and milled
8. Tooth extraction was done on the patient
9. Using the CEREC milled guide the implant was placed and scanned
10. The original planned position was checked with the actual clinical position and adjusted if necessary
11. The custom base was milled using edelweiss i-BLOCK to provide optimum biological seal and emergence profile
12. The crown was milled with edelweiss C-BLOCK
13. The 3 pieces i.e. TiBase + edelweiss Base + edelweiss Crown were put together
14. The immediate loading crown was placed on the implant in the patient's mouth with a torque of 32 Ncm
15. With a control X-ray, the seating was confirmed and occlusion checked with articulation
16. Patient recall and follow up for implant maintenance



Patient case



*Clinical case: Dr. Frederic A. Sakete
BDS, MSc-Implantology & Oral Surgery*

For optimum esthetics, the edelweiss i-BLOCK was first milled as a mesostructure and cemented to the implant abutment. The final crown was milled with edelweiss C-BLOCK A2. This ensured a perfect esthetically driven emergence profile and a biologically driven mucosal seal.



Order Information / Refills

CAD/CAM BLOCK (5 x 12/14/18 mm)

REF 19100	edelweiss CAD/CAM T-BLOCK UNIVERSAL ENAMEL
REF 19101	edelweiss CAD/CAM C-BLOCK A0
REF 19102	edelweiss CAD/CAM C-BLOCK A1
REF 19103	edelweiss CAD/CAM C-BLOCK A2
REF 19104	edelweiss CAD/CAM C-BLOCK A3

CAD/CAM BLOCK WITH ABUTMENT HOLE (5 x 12/14/18 mm, Ø S)

REF 19100.A	edelweiss CAD/CAM i-BLOCK UNIVERSAL ENAMEL
REF 19101.A	edelweiss CAD/CAM i-BLOCK A0
REF 19102.A	edelweiss CAD/CAM i-BLOCK A1
REF 19103.A	edelweiss CAD/CAM i-BLOCK A2
REF 19104.A	edelweiss CAD/CAM i-BLOCK A3

CAD/CAM BLOCK SMALL (5 x 10/12/16 mm)

REF 21100	edelweiss CAD/CAM T-BLOCK UNIVERSAL ENAMEL
REF 21101	edelweiss CAD/CAM C-BLOCK A0
REF 21102	edelweiss CAD/CAM C-BLOCK A1
REF 21103	edelweiss CAD/CAM C-BLOCK A2
REF 21104	edelweiss CAD/CAM C-BLOCK A3

BONDING (5 ml Bottle)

REF 10521	edelweiss VENEER Bond
-----------	-----------------------

NANO-HYBRID COMPOSITE ENAMEL SHADE (10 x 0.3 g Tip)

REF 10301	Enamel
-----------	--------

NANO-HYBRID COMPOSITE DENTIN SHADES (15 x 0.3 g Tip)

REF 10201	Dentin A0
REF 10211	Dentin A1
REF 10221	Dentin A2
REF 10231	Dentin A3

NANO-HYBRID COMPOSITE FLOW (1.5 g Syringe)

REF 13770	Enamel Flowable
REF 10401	Flowable A1
REF 10411	Flowable A2
REF 10421	Flowable A3

EFFECT SHADES (1.5 g Syringe)

REF 13760	Effect Blue
REF 13750	Opaque White
REF 14702	Effect Ice

edelweiss CAD/CAM BLOCKs all come with standard holder attachments - individual holder attachments are available on request, as well as edelweiss CAD/CAM i-BLOCKs with Ø L.



beautiful innovation you can trust

edelweiss dentistry products gmbh • Austria
office@edelweissdentistry.com
www.edelweissdentistry.com



820091/ 2021-08



edelweiss dentistry ® and the edelweiss Logo ® are registered trademarks of edelweiss dentistry products gmbh • Austria

© 2021 edelweiss dentistry products gmbh • Austria. All material contained in this brochure are the property of edelweiss dentistry products gmbh • Austria. No part of this publication may be reproduced, distributed, or transmitted in any form or by any means, without the prior written permission of the edelweiss dentistry products gmbh • Austria. All Rights Reserved.